



# International Journal of Applied Sciences and Biotechnology

A Rapid Publishing Journal

ISSN 2091-2609



**Available online at:**

<http://www.ijasbt.org>

&

<http://www.nepjol.info/index.php/IJASBT/index>

## **Indexing and Abstracting**

CrossRef, Google Scholar, Global Impact Factor, Genamics, Index Copernicus, Directory of Open Access Journals, WorldCat, Electronic Journals Library (EZB), Universitätsbibliothek Leipzig, Hamburg University, UTS (University of Technology, Sydney): Library, International Society of Universal Research in Sciences (EyeSource), Journal Seeker, WZB, Socolar, BioRes, Indian Science, Jadoun Science, Jour-Informatics, Journal Directory, JournalTOCs, Academic Journals Database, Journal Quality Evaluation Report, PDOAJ, Science Central, Journal Impact Factor, NewJour, Open Science Directory, Directory of Research Journals Indexing, Open Access Library, International Impact Factor Services, SciSeek, Cabell's Directories, Scientific Indexing Services, CiteFactor, UniSA Library, InfoBase Index, Infomine, Getinfo, Open Academic Journals Index, HINARI, etc.

**CODEN (Chemical Abstract Services, USA): IJASKD**

Vol-2(2) June, 2014

IC Value: 4.37



For any type of query and/or feedback don't hesitate to email us at: [editor.ijasbt@gmail.com](mailto:editor.ijasbt@gmail.com)



## SYNTHESIS, CHARACTERIZATION AND THERMAL ANALYSIS OF RESINS FROM DIFFERENT CARDANOL BASED DYES

Tapan K. Das

Department of Chemistry, Barchana Women's College, Jajpur, Odisha, India.

Email for correspondence: tapandas.tac@gmail.com

### Abstract

Cardanol (Cashew phenol) is subjected to diazotisation with Aniline and m-Toluidine to get monomers like Cardanol based dye from Aniline (CBDFA) and Cardanol based dye from m-Toluidine (CBDFT). Such monomers have been condensed with formaldehyde in presence of acid catalyst to form resins. The resins have been characterized by FTIR spectra and their thermal behaviour have been studied.

**Key words:** Resin; Cardanol; Formaldehyde; Resin; Aniline; m-Toluidine.

### Introduction


Renewable sources as a substitute to petrochemical derivatives have attracted the attention of many researchers for the synthesis of polymers. Cashew-nut shell liquid (CNSL) a byproduct of cashew industry is a unique natural source of unsaturated long chain phenol (Guo *et al.*, 2002; Petrovic *et al.*, 2005; Roloff *et al.*, 2005; Kong and Narine, 2007; Narine *et al.*, 2007). The phenolic nature of cardanol has promoted researchers to react with formaldehyde or with other aldehyde to produce numerous resinous materials (Phanikumar *et al.*, 2002; Oghome and Kehinde, 2004). In place of cardanol, many workers have synthesized and characterized a number of polymers from cardanol derivatives (Das *et al.*, 1998; Mohapatra *et al.*, 1994; Mishra D.K., Mishra *et al.*, 1996; Nayak *et al.*, 1999; Guru *et al.*, 1999). Cardanol based polymers have wide applications in composites (Tan, 1997; Sathiyalekshmi, 1993), polyurethanes (Sathiyalekshmi and Gopalakrishnan, 2000; Mythili *et al.*, 2004; Das and Lenka, 2011; Athawale and Shetty, 2010), surface coating (Santeusanio *et al.*, 2013) and few others (Unikrishnan and Thachil, 2006; Unikrishnan and Thachil, 2008; Devi and Srivastava, 2006; Devi and Srivastava, 2007). This communication reports on the synthesis, characterization and thermal analysis of resins obtained by condensation of cardanol-based dyes with formaldehyde.

### Experimental

#### Preparation of cardanol based dye from aniline (CBDFA)


4.65gm of aniline was taken in 15ml of distilled water. 13.8ml of conc. HCl was added to it and cooled down to 0-

5 °C. A cold solution of 5gm of sodium nitrite in 10ml of water was added slowly with continuous stirring. To the whole solution a cold solution of 15gm of cardanol in 4ml of 5% NaOH solution was added. A brown red color dye was formed and separated by separating funnel.



#### Preparation of cardanol based dye from m-Toluidine (CBDFT)

5.35gm of m-Toluidine was taken in 15ml of distilled water. 13.8ml of conc. HCl was added to it and cooled down to 0-5 °C. A cold solution of 5gm of sodium nitrite in 10ml of water was added slowly with continuous stirring. To the whole solution a cold solution of 15gm of cardanol in 4ml of 5% NaOH solution was added. A brown red color dye was formed and separated by separating funnel.



#### Synthesis of Resin

The resin was synthesized by condensing cardanol based dyes (CBDFA/ CBDFT) (4 mmol) with formaldehyde (40 mmol) in presence of 1% hydroquinone and 2 ml of 6 N HCl at 90°C for 4 – 6 hours with periodical shaking. After completion of the reaction, the product was repeatedly



washed with hot water in order to drive out unreacted materials. The product was finally dried in vacuum at 60 °C.

The physico-chemical properties of the resins are furnished in Table 1.

**Table 1:** Physico – Chemical Properties of Resins

Sample	System	Yield (%)	Colour	Structure	Solubility
Resin – 1	CBDFA-FORMALDEHYDE	71	Reddish Brown	Crystalline	Toluene, DMF
Resin – 2	CBDFT -FORMALDEHYDE	69	Reddish Brown	Crystalline	Toluene, DMF

### Reaction Scheme



**Table 2:** Thermal Decomposition of Resins

Sample Code	Composition	% Weight loss at various temperature						
		100°C	200°C	300°C	400°C	500°C	600°C	700°C
Resin 1	CBDFA-FORMALDEHYDE	1.7482	5.5944	20.6293	34.9656	64.3356	68.8808	76.9230
Resin 2	CBDFT-FORMALDEHYDE	2.0979	3.8461	19.9300	34.2657	65.7342	69.930	79.7202

## Results and Discussion

### FTIR Spectra

Fourier transform infrared (FTIR) spectra of Resin- 1 and Resin -2 are shown in Fig. 1(a) and 1(b) respectively.




Fig. 1a: Fourier transform infrared (FTIR) spectra of Resin 1.




Fig. 1b: Fourier transform infrared (FTIR) spectra of Resin 2.

The interaction between chemical groups on either the same or different molecules can cause a shift of the IR peak positions of the participating groups, which is commonly observed in macromolecular system due to the existence of hydrogen bonds (Lu and Zhang, 2002). The peaks such as  $3500 - 3300 \text{ cm}^{-1}$  (O - H hydrogen bonded),  $3100 - 3000 \text{ cm}^{-1}$  (aromatic C - H stretching),  $2924 - 2855 \text{ cm}^{-1}$  (Symmetric C - H stretching),  $1590 \text{ cm}^{-1}$  (C  $\equiv$  C stretching of aromatic ring) and a peak at  $1428 \text{ cm}^{-1}$  is due to  $\text{-N=N-}$  stretching of azo group.

### Thermo gravimetric analysis of the Resins

The thermo gravimetric analysis in Table 2 reveals that the resins decomposed in three distinct steps. In the first step of thermal degradation  $100 - 200^\circ\text{C}$  weight loss up to 5% is observed in Resin 1 & 2 (Fig. 2a and 2b). This may be attributed to the removal of moisture retained in the resin. A gradual weight loss occur in the temperature ranges  $200 - 400^\circ\text{C}$  may be caused by thermal degradation of the small fragments like  $\text{CH}_3$ , OH and the side chain. The resins are thermally more stable up to  $400^\circ\text{C}$ . The weight loss around 80% in the last stage of thermal degradation may be due to the depolymerisation and the cleavage of the aromatic ring in an oxydegradative manner.




Fig. 2a: Thermal degradation of weight in Resin 1




Fig. 2b: Thermal degradation of weight in Resin 2.

## Conclusion

The structure of the resin is established by FTIR study. The kinetic study shows that due to presence of azo group in the resins, the decomposition temperature is enhanced. The resins show good thermal stability up to  $400^\circ\text{C}$ . The resin of cardanol based dye from m-toluidine has comparatively greater percentage of weight loss due to low degree of polymerization.

## References

- Athawale V and Shetty N (2010) Synthesis and characterization of low cost cardanol polyurethanes. *Pigment and Resin Technology*. **39**: 9-14. DOI: 10.1108/03699421011009546
- Das D, Nayak PL and Lenka S (1998) Interpenetrating polymer networks derived from castor oil isophorone diisocyanate cardanyl acrylate/cardanyl methacrylate- Thermal and XRD studies. *Polym. Plast. Tech. Eng.* **37**: 419-426. DOI: 10.1080/03602559808001370
- Das TK and Lenka S (2011) Thermal and X-ray diffraction studies on interpenetrating polymer networks of castor oil-based polyurethane and cardanol based dyes. *Polym. Plast. Tech. Eng.* **50**: 481-484. DOI: 10.1080/03602559.2010.543241
- Das TK, Das D, Guru BN, Das BN and Lenka S (1998) Synthesis, characterization and thermal studies of semi-interpenetrating polymer networks derived from castor oil based polyurethane and cardanol derivatives. *Polym. Plast. Tech. Eng.* **37**: 427-435. DOI: 10.1080/03602559808001370

- Devi A and Srivastava D (2006) Cardanol-based novolac-type phenolic resins. I. A kinetic approach. *J. Appl. Polym. Sci.* **102**: 2730-2737. DOI: 10.1002/app.24363
- Devi A and Srivastava D (2007) Studies on the blends of cardanol-based epoxidized novolac type phenolic resin and carboxyl-terminated polybutadiene (CTPB). *Matter Sci. Eng.* **458**, 336-341 DOI: 10.1016/j.msea.2006.12.081
- Guo A, Demydov D, Zhang W and Petrovic ZS (2002) Polyols and polyurethanes from hydroformylation of soybean oil. *J. Polym. Environ.* **10**: 49-52. DOI: 10.1023/A:1021022123733
- Guru BN, Das TK and Lenka S (1999) Studies on synthesis, characterization and thermal properties of resins derived from cardanyl acrylate-furfural-organic compounds. *Polym. Plast. Tech. Eng.* **38**: 179 – 187. DOI: 10.1080/03602559909351569
- Kong X and Narine SS (2007) Physical Properties of Polyurethanes Plastic Sheets Produced from Polyols from Canola Oil. *Biomacromolecules.* **8**: 2203-2209. DOI: 10.1021/bm070016i
- Lu Y and Zhang L (2002) Morphology and mechanical properties of semi-interpenetrating polymer networks from polyurethane and benzyl konjac glucomannan. *Polymers*, **43**: 3979 – 3986. DOI: 10.1016/S0032-3861(02)00206-9
- Mishra DK, Mishra BK, Lenka S and Nayak PL (1996) Thermal properties of the semi-interpenetrating polymer networks composed of castor oil polyurethanes and cardanol-furfural resin. *J. of Polymer Engineering and Science.* **36**: 1047-1051. DOI: 10.1002/pen.10493
- Mohapatra NK, Lenka S and Nayak PL (1994) Thermal properties of copolymers derived from semicarbazone of 4-hydroxyacetophenone-furfural-substituted benzoic acids. *Thermochim. Acta.* **241**: 51-56. DOI: 10.1016/0040-6031(94)87006-3
- Mythili CV, Malar Retna A and Gopalkrishnan S (2004) Synthesis, mechanical, thermal and chemical properties of polyurethanes based on cardanol. *Bull matter Sci.* **2**: 235-241.
- Narine SS, Kong X, Bouzidi L and Sporns P (2007) Physical properties of polyurethanes produced from polyols from seed oils. *J. Am. Oil Chem. Soc.* **84**: 65–72. DOI: 10.1007/s11746-006-1008-2
- Nayak SS, Das SK and Lenka S (1999) Synthesis and characterization of copolymers from cardanyl acrylate and vinyl monomers. *React. Funct. Polym.* **40**, 249-254. DOI: 10.1016/S1381-5148(98)00046-7
- Oghome P and Kehinde AJ (2004) Separation of cashew nut shell liquid by column chromatography. *African journal of science and technology (AJST).* **5**: 92-95.
- Petrovic ZS, Zhang W and Javni I (2005) Structure and properties of polyurethane. *Biomacromolecules*, **6**: 713-719.
- Phanikumar P, Paramashivappa R, Vithayathil PJ, SubbaRao PV and SrinivasaRao A (2002) Process for Isolation of Cardanol from Technical Cashew Nut Shell Liquid. *J. Agric. Food. Chem.* **50**: 4705-4708. DOI: 10.1021/jf020224w
- Roloff T, Erkens U and Höfer R (2005) Polyols based on renewable feedstocks: A significant alternative, *Urethanes Technology*, **22**: 29-33.
- Santeusanio S, Attanasi OA, Majer R, Cangiotti M, Fattori A and Ottaviani MF (2013) Effect of hydrogenated cardanol on the structure of model membranes studied by EPR and NMR. *Langmuir*, **29**: 11118-11126. DOI: 10.1021/la402008n
- Sathiyalekshmi K (1993) Studies on structure and properties of CNSL novolac resins prepared with succinic acid catalyst. *Bull matter Sci.* **16**: 137-150.
- Sathiyalekshmi K and Gopalakrishnan S (2000) Synthesis and characterisation of rigid polyurethanes based on hydroxyalkylated cardanolformaldehyde resin. *Plast. Rubber compos.* **29**: 63-69.
- Tan TTM (1997) Thermoplastic composite based on jute fiber treated with cardanol formaldehyde. *Polym. Compos.* **5**: 273-279.
- Unikrishnan KP and Thachil ET (2006) The modification of commercial epoxy resin using cardanol-formaldehyde copolymers. *Int. J. Polym, Matter.* **55**: 323-338
- Unikrishnan KP and Thachil ET (2008) Studies on the Modification of Commercial Epoxy Resin using Cardanol-based Phenolic Resins. *J. Elast. Plast.* **40**: 271-286. DOI: 10.1177/0095244307086712